



ACTION™ MAGNET Magnetic Base for XMR-Xcel Magnetic Receptive Media



ACTION™ Magnet is the matched magnetic base component for XMR™ - Xcel Magnetic Receptive Media. In most applications, this permanently magnetized material is installed once and is the base for the magnetic receptive graphics. It is also 100% compatible with all known magnetic receptive media and guaranteed with the same performance as the InvisiLock® products. There are several variations of ACTION™ Magnet for different applications. If needed, we can customize a product for a specific application and also convert to sheets or custom roll sizes.

30-mil Standard Energy with Indoor Adhesive

- Hi-tack permanent adhesive great for mounting to smooth surfaces or creating your own backer boards
- Supports multiple layers of XMR™ - Xcel Magnetic Receptive Media
- Standard Roll: 24.375" x 50' (Custom rolls and sheets available upon request)

30-mil High Energy with Indoor Adhesive

- Hi-tack permanent adhesive great for mounting to smooth surfaces or creating your own backer boards
- Supports multiple layers of XMR™ - Xcel Magnetic Receptive Media
- Standard Roll: 24.375" x 50' (Custom rolls and sheets available upon request)

40-mil High Energy Double-Sided

- Magnetized on both sides of the sheet for application to metal fixtures or magnetic receptive surfaces without the use of adhesives
- Supports multiple layers of XMR™ - Xcel Magnetic Receptive Media
- Standard Roll: 24.375" x 50' (Custom rolls and sheets available upon request)

- *Adhesive backed magnet is not intended for application to painted drywall or other textured surfaces.*
- *We recommend magnetic receptive paint and high energy double-sided magnet for direct to wall applications.*

STANDARD SPECIFICATIONS	30-Mil Standard Energy	30-Mil High Energy	40-Mil High Energy
Minimum Strength (pull/lbs per sq ft at 0 air gap)	95	150	165 each side
Gauss (at 0.25" gap)	<1	<1	<1
Gauss (at 2 meters)	0	0	0

PRODUCT SAFETY: Action Magnet is ferrite-based and poses no health or safety issues. This type of magnet does not emit a strong magnetic field therefore does not cause interference or damage to pace makers, monitors or other electronic equipment. Due to the low gauss emission, it is not labeled as magnetized material per IATA (International Air Transportation Association) definition and therefore can be air shipped in bulk quantity.

All images, registered trademarks and trademarks are property of their respective owners

Information provided here is based on research and is believed to be reliable as of printing date. This information does not constitute a warranty. All material should be tested by purchaser to determine final suitability. Quality Media will not be held responsible for customers end use of product. Quality Media is available for directions and advice as to proper use and application of our products.



ACTION MAGNET™



ACTION™ MAGNET Magnet and Surface Preparation / Adhesive Specifications

ACTION™ Magnet Preparation and Considerations

Lay flat: Rolled magnet has a curl “memory” that will relax over time. Magnet **MUST** lay flat prior to installation. Magnet must be unrolled, placed with the curled side down and allowed to lay flat for a minimum of 60 minutes, but preferably overnight. Trying to install the magnet with curl (pulling away from the surface), combined with the weight of the magnet, will increase the chance of adhesion failure.

Temperature: To accelerate adhesion to the substrate, it is crucial that the adhesive-backed magnet be warmed to 50° F or higher.

Weight: Magnet is generally heavy. Use caution and proper lifting techniques when moving or working with this material.

Tiling: It is recommended that panels be applied with a slight gap (1/32” to 1/16”). The gap allows the XMR™ to span over this seam with little or no visible affect. Butt seaming, can introduce a ridge or tenting that might be visible in the magnetic receptive layer(s). Even though it may appear flat initially, subtle movement in the magnet or the substrate may occur over time, making the defect more visible.

Surface Preparation: The intended application surface must be clean of dirt, dust, grease, and other contaminants. The risk of adhesive failure is significantly increased when not applying to a properly prepared surface. It is the responsibility of the purchaser and installer to prepare and test all intended surface(s) for adhesion prior to final installation.

Adhesive backed magnet is not intended for application to painted drywall or other textured surfaces. Magnetic receptive paint and high energy double-sided magnet is recommended for direct to wall applications.

STANDARD INDOOR ADHESIVE

An aggressive, general purpose, rubber-based pressure sensitive adhesive with a thin polyester carrier. The carrier film provides dimensional stability and superior die cutting properties. Typically used for bonding to metal, plastics and most low or unplasticized substrates. The liner is 60# densified, semi-bleached kraft paper.

PHYSICAL PROPERTIES	Typical Value	U/M	Test Method
Quick Tack on Stainless Steel	10.0	Lbs/Sq In	CTM-25
Peel Adhesion on Stainless Steel (30 minutes)	8.0	Lbs/In	PSTC-3
Shear on Stainless Steel (1000 g/sq in @ 72°F)	300+	Hours	PSTC-7
Adhesive Thickness with PET Carrier	.0029	Inches	Caliper
Application Temperature Range	Above 50	°F	-
Service Temperature Range	0 - 150	°F	-

Adhesive Shelf Life: Two years when stored at 75°F and 50% relative humidity

These typical results are based on test procedures which are believed to be reliable. Due to variable conditions or methods of processing, any resellers implies NO GUARANTEES OR WARRANTIES ARE EXPRESSED OR IMPLIED INCLUDING THE IMPLIED WARRANTY OF MERCHANTABILITY AND FITNESS FOR A SPECIFIC PURPOSE, nor any recommendations made to infringe on any patents.

Information provided here is based on research and is believed to be reliable as of printing date. This information does not constitute a warranty. All material should be tested by purchaser to determine final suitability. Quality Media will not be held responsible for customers end use of product. Quality Media is available for directions and advice as to proper use and application of our products.