



DuraVinyl 435 - Barricade Vinyl

Product Description

3.5-mil premium calendered vinyl consists of a flexible, semi-gloss film having excellent weathering and aging characteristics. Used for decorative striping, transportation markings, flat surface, product identification and warning decals. High-tack adhesive for low energy surfaces.

Uses

- Decorative striping
- Transportation markings
- Product identification
- Warning decals
- Cut Vinyl Letters
- Plywood Barricades

Features and Benefits

- Suitable for low surface energy substrates
- Recommended for flat, dry surfaces

Size	Catalog #
54" x 150'	0943554
60" x 150'	0943560

Ordering

DuraVinyl 435 is a Quality Media and Laminating Solutions exclusive product. It is stocked in all of our distribution centers and available for immediate delivery.

To place an order, call us at 1-800-552-9427.

Information provided here is based on research and is believed to be reliable as of printing date. This information does not constitute a warranty. All material should be tested by purchaser to determine final suitability. Quality Media will not be held responsible for customers end use of product. Quality Media is available for directions and advice as to proper use and application of our products.

Specifications

Face Material	3.5 mil premium calendered vinyl
Color and Finish	Semi-gloss white
Adhesive	2 mil High tack permanent acrylic
Liner	90# polycoated bleached layflat
Minimum Application Temperature	40°F
Service Temperature Range	-40°F to +180°F
Shelf Life	2 years @ 73°F, 50% RH
Outdoor Durability	5 years

Application to Plywood Specifications

Application to outdoor plywood:

Always seal the top edge of the graphic with a clear silicone bead or wrap the graphic over the plywood.

This will prevent water from wicking and extend the life of the graphic.

Typical Characteristics

Average Adhesion Values	15 min.	24 hr.
(PSTC-1, 180° peel @ 12"/min., 73°F, on Stainless Steel)	8.5lbs	9.5lbs

Chemical Resistance

Distilled Water (24 hr) No Effect
 Detergent (24 hr) No Effect
 10% HCl (10 min) No Effect
 10% Ammonium Hydroxide (10 min) No Effect
 Anti-Freeze (24 hr) No Effect
 SAE 20 motor oil (24 hrs) No effect
 Gasoline (1hour) No effect